8th International Conference "Nanotechnologies and Nanomaterials" NANO-2020



ZINC OXIDE NANOPARTICLES: FEATURES OF OBTAINING **AND PROPERTIES**

Bondar O.O.¹, Fesych I.V.¹, Voitenko T.A.¹, Nedilko S.A.¹, Dziazko O.G.¹, Zelenko M.A.¹, Chukova O.V.¹, Nedilko S.G.¹, Liedienov N.A.^{2,3}, Pashchenko A.V.^{2,3,4}, Levchenko G.G.^{2,3}

¹ Taras Shevchenko National University of Kyiv, Lva Tolstoho Str., 12, Kyiv-01033, Ukraine. Corresponding author - Bondar O.O.; e-mail: alionka-15@ukr.net

² International Centre of Future Science, State Key Laboratory of Superhard Materials of Jilin University, Qianjin Str., 2699, Changchun-130012, China. ³ Phase Transitions Department, Donetsk Institute for Physics and Engineering named after O. O. Galkin, NASU, Prospect Nauki, 46, Kyiv-03028, Ukraine. ⁴ Institute of Magnetism, NASU and MESU, 36-b Vernadsky Blvd., Kyiv-03142, Ukraine.

INTRODUCTION

Zinc oxide nanopowders are an important metal oxide with unusual^{100.00} semiconducting properties and wide application in various fields, such as catalysis, optic, pigment, piezoelectric devices, chemical sensors, cosmetic 80.00 ingredients, medicine. Due to the large numerous of toxic chemicals and extreme environment employed in the chemical production of ZnO nanopowders, green chemistry methods employing the use of different 60.00biological materials (plants, fungus, bacteria, algae) and natural polymers (gelatin, starch, different proteins) have been adopted. Besides that, the use of natural sources in the synthesis of nanomaterials can have a low cost and ecofriendly approach.



We studied the green chemical approach for fabrication method using natural 20.00 polymer and the physical and chemical characteristics of zinc oxide nanopowders.

MATERIALS AND METHODS

ZnO nanopowders were synthesized by sol-gel technique with gelatin as a green stabilizer. Deionized water was used as solvent. The zinc nitrate solution was added to the gelatin solution, and the container was moved to a water bath. The temperature of the water bath was fixed at 80 °C. Stirring was continued for 12 h to obtain a brown gel. The final product was calcined at 500, 600 and 700 °C in air for 8 h to obtain ZnO nanoparticles.

RESULTS AND DISCUSSION

The thermogravimetric curve of the ZnO nanopowder synthesized by the solgel method in a gelatin environment are presented in Fig.1. The TG curve descends until it becomes horizontal around 500 °C. No weight loss between 500 and 600 °C was detected on the TG curve, which indicates the formation of nanocrystalline ZnO as the decomposition product.

All the diffraction peaks can be assigned to hexagonal phase with Wurtzite structure with space group (P63mc). Crystallite sizes and lattice strain were studied by using Williamson-Hall method. The estimated crystallite size in synthesized samples ranged from 22 to 100 nm. The luminescence properties of becomes main mechanism for such synthesis conditions obtained nanoparticles were investigated.

Fig.3. XRD pattern and Williamson-Hall analysis of ZnO nanopowders prepared in gelatin media prepared at different calcinations temperature.

/00 -	1	12112-0	
		050	





Fig.2. Oriented consolidation (attachment) of ZnO nanoparticles: (A) HRTEM image, calcinations temperature 500 $^{\circ}C$, (B) scheme of mechanism.

Oriented attachment mechanism to our opinion in the temperature range 500 - 700 °C and is accompanied by notable particle growth (Fig. 2).

1000

0.007 -



- According to X-ray and thermal analysis, single-phase zinc oxide is formed already at 500 °C.
- The tensile strain and the particle size increase with an increasing the heating temperature from 500 °C to 700 °C.
- The particles size and the crystals structure defects, which leads to the appearance of lattice stresses are influence to the X-Ray peak broadening.