



1D polaritons in macroporous silicon with nano-coatings

Liudmyla A. Karachevtseva, Oleg O. Lytvynenko, Olena Y. Sapelnikova

V. Lashkaryov Institute of Semiconductor Physics of NASU, Prsp. Nauki, 41, Kiev-03028, Ukraine
lakar@isp.kiev.ua



1. INTRODUCTION

Macroporous silicon structures prepared by photoanodic etching are one of the promising materials for the development of 2D photonic crystals and for the measuring of photonic band gaps. Presence of periodically located cylindrical macropores provides large effective macropore surface and enhanced photo-physical characteristics of macroporous silicon. Franz-Keldysh oscillations in the electroreflectance spectra of macroporous silicon structures without nano-coatings in the area of direct band-to-band transition were measured. At the wavelengths, compared with the optical period of the macroporous silicon structures, the measured IR absorption is two orders of magnitude higher of the silicon single crystal. The formation of steps and the change in optical absorption by the 3/2 law confirmed realization of the impurity Franz-Keldysh effect. In addition, for 2D macroporous silicon structures with coatings of surface nanocrystals, oscillations of IR absorption increase to maximal amplitudes in the spectral region of surface states. The dependence of the oscillation maxima on its number is linear with a constant period. The analysis of IR absorption oscillations was performed within the model of resonant scattering of electrons on surface states in a strong electric field with a difference between two resonant energies equal to the Wannier-Stark step $\Delta E = Fa$ (F – the electric field strength, and a – the silicon lattice constant). The shift and deviations of oscillation peaks, the broadening parameter Γ of the Wannier-Stark ladders and the influence of “quantum superiority” on coherence of Wannier levels were analyzed too.

In this work, we investigated high-resolution optical absorption spectra of 2D macroporous silicon structures with nano-coatings. We performed a comparative analysis of the results on electro-optical effects in macroporous silicon of 1D and 2D exciton-polaritons on macropores. Here we achieved excellent parameters of 1D exciton-polaritons at room temperature for highcoherent optical phenomena implementations in quantum computers, lasers and metamaterials.

3. EXPERIMENT AND DISCUSSION OF RESULTS

Comparison of the absorption spectra of our structure show that after changing resolution of measurement from 2 cm^{-1} to 1 cm^{-1} the period of oscillations in optical absorption spectra decreases by 3 times and the optical absorption increases by $60 \div 100$ times. Giant two-polar oscillations of the absorption appear in the spectral region of Si-Si bonds and in the $5500 \div 7500 \text{ cm}^{-1}$ spectral region of P_b centers. Si-Si-bonds represent the transverse fluctuations of silicon atoms on the surface of the macropores, i.e., transverse phonons.

In general, the interaction of an external electromagnetic field with dipole-active states leads to polariton formation. These resonances lead to the splitting of surface polaritons and to the appearance of the slits in its spectrum with width proportional to $(d/\lambda)^2$. Table shows minimal value of $d/\lambda = (0.625 \div 3) \cdot 10^{-3} \ll 1$ and small splitting of surface polariton modes, equal to $6 \div 14 \text{ cm}^{-1}$ for structures #2 and #3 (Fig. 1a, b). It is proportional to $(d_2/d_3)^{1/2}$, where $d_2 = 20 \text{ nm}$ and $d_3 = 20+28 = 48 \text{ nm}$. So, for 2D macroporous silicon structures with nano-coatings surface polaritons are formed at boundary Si-SiO₂ for samples #1, and at boundaries Si-SiO₂ and SiO₂+“PEI-ncCdS” for samples #2 and #3 (Table). The results obtained are fully consistent with data for phonon polaritons in microresonators.

Measurements the giant two-polar oscillations with very small half-width 0.5 cm^{-1} and Rabi frequency 1.0 cm^{-1} (Table) testify the strong interaction of surface polaritons with photons. Moreover, by changing the thickness of the nano-coatings, it is possible to achieve a match in the frequency of interference modes with frequencies of slit oscillations of surface bonds on boundaries Si-SiO₂ and SiO₂+“PEI-ncCdS”. When the frequencies of local oscillations of surface bonds and slit modes matched, then the light absorption increases up to 10^7 times on the frequencies of slit oscillations of surface bonds.

Earlier we observed the oscillating structure in the absorption spectra of macroporous silicon structures with surface nanocrystals. The form of oscillations and constant oscillation period indicate the resonant character of scattering (the Wannier-Stark electro-optical effect). According to method of experimental observation of Wannier-Stark ladders, the scattering amplitude has resonant behavior at electron scattering on impurities.

The wave function in the Wannier representation is:

$$\langle j | \Psi_E \rangle = \langle j | \Phi_E \rangle + \frac{\langle j | \hat{G}_0(E) | 0 \rangle V_0 \langle 0 | \Phi_E \rangle}{1 - V_0 \langle 0 | \hat{G}_0(E) | 0 \rangle} \quad (1)$$

Here the first (second) term describes the incident wave (scattered waves); j – numbers the lattice site, $\hat{G}_0(E)$ is the Green operator,

V_0 is the impurity potential. The complex energies of resonances in electron scattering are $1/V_0 = \langle 0 | \hat{G}_0(E) | 0 \rangle$ (2)

at $E = \varepsilon - i\Gamma$ ($\Gamma > 0$). The difference of two neighboring resonance energies is equal approximately to the value of the step in the Wannier–Stark ladder. The dispersion law is considered in form:

$$E(k) = E_0 - (\cos k_x a + \cos k_y a), \quad (3)$$

where k is a quasi-momentum with components k_x, k_y, E_0 is the energy corresponding to the midgap, Δ – the energy equal to 1/6 of the band gap, a – Si lattice parameter.

In our case, an electric field of “silicon-nano-coating” heterojunctions on the macropore surface is directed perpendicularly to the macropore surface (Fig. 2a), and surface states that scatter electrons are concentrated perpendicularly to the x -direction in the plane (y, z) , that is the plane of resonant scattering. After illumination, electrons are accelerated in the electric field of the enriched electric potential (Fig. 2b), oscillate and scatter by surface states in the radial direction x relative to the macropore, in the plane (y, z) (Fig. 2a), which is the plane of resonance scattering with infinity amplitude. It results in additional vertically polarized light in z direction and horizontally polarized light in x direction and the infinity growth of dielectric constants and corresponding changes in IR absorption at room temperature.





Fig. 4. Fragments of optical absorption of sample #1 a – measured with a resolution of 1 cm^{-1} in spectral area $5000\text{--}8000 \text{ cm}^{-1}$ of P_b centers; b – theoretical calculations by the secant function.

For 2D macroporous silicon structures with nano-coatings, band bendings on the surface of the macropores are significant (Fig. 2b). Under these conditions, surface polaritons interact with photons strongly due to resonances of dipole-active vibrations and surface modes at boundaries Si-SiO₂ and SiO₂+“PEI-ncCdS” on macropores. Shape of oscillations corresponds to the interference of polaritons as the eigenstates of the system “nano-coating – silicon matrix – waveguide modes” (Fig. 3). In our case, an additional degree of freedom due to creation of vertically polarized light in z direction and horizontally polarized light in x direction (Fig. 2a) permit to interpret the obtained result as two-photon interference – Hong-Ou-Mandel effect. In this case, macropore is a beam splitter (BS) with maximum and minimum coincidences for measurements with parallel and perpendicularly polarizations, respectively. Beam splitter includes input ports A and B, and output ports labelled C and D. The four ways of the two photons can exit from the beam splitter through the same port or different ports. Two-photon states corresponded to photons exiting through the same output ports demonstrate constructive interference (bosonic behavior). The two-photon states corresponding to photons exit through the different output ports demonstrate destructive interference (fermionic behavior).

In case, presented in Fig. 3, we observed the “constructive” interference of the two-photon states corresponded to photons exited through the same output ports C and D (Fig. 2b, bosonic behavior). Maximum coincidences for measurements of the IR absorption spectrum of macroporous silicon structures with surface ZnO nanocrystals (Fig. 3, curve 1) and the same spectrum of IR absorption, moved for 2 period (Fig. 3, curve 2) confirmed the high coherence of “constructive” interference of the two-photon states.

In addition, we measured giant two-polar oscillations of the absorption in spectra of Fig. 1 and Fig. 2 at TO-vibrations of Si-Si-bonds and P_b centers. Interaction of TO phonons with the scattered electrons in z direction (Fig. 2b) enhances k_z – vibrations, and the dispersion law (3) transforms to $E(k) = E_0 - (\cos k_x a)$. Amplitude of the resonance scattering became dependent on the secant function $(\cos k_x a)^{-1} = \sec k_x a$, and the slit-like modes are formed on boundaries “silicon matrix – nano-coatings”. Fig. 4a, b show fragments of optical absorption for sample #1 and a resolution of 1 cm^{-1} : a – in spectral area of P_b centers; b – theoretical calculations the secant function. Fig. 4a, b confirms qualitatively the model of the two-polar giant oscillations in optical absorption spectra depended on the function $\sec k_x a$. In this case, the two-photon waves exit from the beam splitter through the different ports, and we observe destructive interference of the two-photon states corresponding to fermionic behavior of two-polar oscillations.

It means that 2D resonances of Wannier-Stark electro-optical effect in yz plane (Fig. 3) transforms into 1D resonances in one direction z of surface waves (Fig. 4) and into the one dimensional (1D) polaritons. Such transformation results in the giant amplitudes of absorption oscillations ($\pm 10^7$ arb.un.) and measurements the ultra-small half-width of oscillations ($0.5 \pm 0.1 \text{ cm}^{-1}$) and minimal Rabi frequency of samples (1.0 cm^{-1}) equal to resolution of spectral measurement (Table).

2. PROCEDURE

The samples to be studied were made of silicon wafers with thickness $H = 520 \mu\text{m}$, resistivity of $4.5 \Omega \cdot \text{cm}$, characterized by the (100) orientation and n -type of conductivity (the electron concentration $n_0 = 10^{15} \text{ cm}^{-3}$). We used the technique of electrochemical etching at the backside illumination of a silicon substrate. Macropores were etched in the form of a square lattice of parallel air cylinders with diameter $D_p = 2 \pm 0.2 \mu\text{m}$, period $4 \mu\text{m}$, depth $h_p = 50 \div 100 \mu\text{m}$, and concentration $N_p = 6.25 \cdot 10^6 \text{ cm}^{-2}$. Addition anisotropic etching in 10 % solution of KOH permits to remove microporous layers from the macropores surface. SiO₂ nano-coatings were formed in the diffusions to ve after treatment of macroporous silicon substrates in the nitrogen atmosphere. The oxide layers (thickness of 10 and 20 nm) were obtained on macroporous silicon samples in dry oxygen during $40 \div 60 \text{ min}$ at the temperature of 1050°C . The oxide thickness was measured using ellipsometry. CdS nanoparticles of 1.8–2 nm in size were deposited on the oxidized surface of macropores from the colloidal solutions in polyethyleneimine (PEI). ZnO nanoparticles were synthesized from solution of zinc acetate of $\text{Zn}(\text{CH}_3\text{COO})_2$ in ethanol and deposited on the oxidized surface too.

Table shows the parameters of nano-coatings on 2D macroporous silicon structures. We performed optical investigations within the spectral range $300 \div 7800 \text{ cm}^{-1}$ by using an IR Fourier spectrometer PerkinElmer Spectrum BXII. High-resolution optical absorption spectra were measured in the $200 \div 8500 \text{ cm}^{-1}$ spectral range on a spectrometer BrukerVertex70V with a resolution of 1 cm^{-1} . The optical absorption spectra were measured at normal incidence of IR radiation on a sample (along the cylindrical macropores) in the air at room temperature.

No of sample	Boundary “Si – nano-coating”	Thickness d_1 of SiO ₂ layer, nm	Thickness d_2 of “PEI-ncCdS”, nm	d/λ	$(d/\lambda)^2$	Splitting of surface modes, cm^{-1}	Rabi frequency, cm^{-1}
1	Si-SiO ₂ +“PEI-ncCdS”	10	16	$6.25 \cdot 10^{-4}$	0.025	–	1.0
2	Si-SiO ₂ +“PEI-ncCdS”	20	16	$1.25 \cdot 10^{-3}$	0.0353	6	1.0
3	Si-SiO ₂ +“PEI-ncCdS”	20	28	$3.0 \cdot 10^{-3}$	0.055	14	1.0
4	Si-SiO ₂ +“PEI-ncZnO”	20	28	–	–	–	1.0




Fig. 1. The optical absorption by 2D structures of macroporous silicon with nano-coatings: a – sample #2, b – sample #3 from Table measured at resolution of 1 cm^{-1} near Si-Si-bonds.




Fig. 2. a – a fragment of the macroporous silicon structure with the nanocoating with the radius of macropore R and the surface nanocoating thickness d ; b – beam splitter with input and output ports. Scheme of band bending on the surface of macropores between macroporous silicon matrix with Fermi level E_F and layers ncCdS and SiO₂ (circles – electrons and holes, lines – impurity states)




Fig. 3. Dependences of the IR absorption of macroporous silicon structures with surface ZnO nanocrystals (structure #4) in the spectral range $500\text{--}1500 \text{ cm}^{-1}$ (1), the same spectrum of IR absorption, moved for 2 period (2).

4. CONCLUSIONS

1D polaritons with the giant two-polar oscillations in IR absorption spectra of macroporous silicon with nano-coatings were measured. The generated photoelectrons link heavily with holes in the macropore potential pits forming 2D interference polaritons at room temperature. Increase the resolution of IR spectra measurements to 1 cm^{-1} resulted in generation of dipole-active vibrations and change of dispersion law in yz plane of macropore surface to z direction along macropores. Thus, 2D polariton transforms into 1D polariton according to secant law in spectral area of TO-vibrations of Si-Si-bonds and P_b centers.

Surface polaritons interact with photons strongly due to resonances of dipole-active vibrations and surface modes at boundaries Si-SiO₂ and SiO₂+“PEI-ncCdS” on macropores. Shape of oscillations corresponds to the interference of polaritons as the eigenstates of the system “nano-coating – silicon matrix – waveguide modes”. In our case, the vertically polarized light along macropores (z direction) and horizontally polarized light (x direction) permit the explanation of results as two-photon interference (the Hong-Ou-Mandel effect). In this case, macropore is a beam splitter (BS) with maximum and minimum coincidences for measurements with parallel and perpendicularly polarizations, respectively. Beam splitter includes input ports A and B, and output ports labeled C and D. The four ways of the two photons can exit from the beam splitter through the same port or different ports. We observed constructive interference of the two-photon states corresponding to photons exiting through the same output ports (bosonic behavior). Furthermore, 1D polaritons are perspective for high-coherent optical quantum computers on macroporous silicon with nano-coatings, for lasers and new metamaterials.