

THE ANTICORROSION PERFORMANCES OF THE ZEOLITE/Zn(H₂PO₄)₂ PIGMENT FOR ALUMINIUM ALLOY

Danyliak M.-O.M., Khlopyk O.P., Zin I.M., Korniy S.A. Karpenko Physico-Mechanical Institute, NAS of Ukraine, Lviv, Ukraine

The *aim* of work was to study the corrosion inhibition of aluminium alloy by anticorrosive pigments obtained by mechanochemical modification of nanoporous zeolite.

Synthesis: Zeolite/ $Zn(H_2PO_4)_2$, pigment was obtained by mechanochemical modification using high-energy Retsch PM 100 planetary mill. The weight ratio in the grinding mixture between dihydrogen phosphates and zeolite NaA was 1:3, 1:1, 3:1. Due to modification of the zeolite at 200 rpm for 1 h (Fig. 1), there is a redistribution of the X-ray signal intensities, which indicates a change in their structure and may be associated with the introduction of phosphate into pores of For zeolite modified with zeolite. the zinc monophosphate, at 400 rpm for 2 h, the crystal lattice is completely destroyed and the amorphous phase increased. To obtain pigments based on zeolites and phosphates, a necessary condition is the preservation of the structure of the aluminosilicate framework, in the pores of which nanosized particles of corrosion inhibitors can be intercalated. Therefore, the optimal duration of mechanochemical processing is 1–2 h at a rotational speed of the cylinder of the planetary mill of 200 rpm, since the crystalline structure of NaA zeolite is preserved under such maiting

Results and discussion: The zeolite/ $Zn(H_2PO_4)_2$ pigments effectively reduce the corrosion current of the aluminium alloy. The corrosion resistance of the alloy is significantly increased in the solution with the pigment extract compared to the noninhibited solution. The highest anti-corrosion effect is established for zeolite/ $Zn(H_2PO_4)_2$ pigment with a concentration of 1 g/l at a 1:1 components ratio, probably due to optimal solubility of its phosphate phase.



Fig. 2 Polarization curves of D16T aluminium alloy after 3 and 96 h (b) exposure in: 1 - 0.1% NaCl solution and with the addition of the pigment (1 g/l) at different zeolite/Zn(H₂PO₄)₂ ratios: 2 - 3:1; 3 - 1:1; 4 - 1:3



Fig. 1 XRD of modified zeolite at 200 rpm: 1h (*a*) and 2 h (*b*)

Fig. 3 Impedance modulus dependencies for D16T alloy after 24 h exposure in: 1 - 0.1%NaCl solution and inhibited by 1 g/l of: 2 – unmodified zeolite and at different zeolite/Zn(H₂PO₄)₂ ratios: 3 - 3:1; 4 - 1:1; 5 - 1:3



The impedance modulus $Z_{0.1}$ at a frequency of 0.1 Hz for samples of aluminium alloy after 3 h exposure to chloride solution with 1 g/l of unmodified zeolite are the lowest (about 4.1·10³ Ohm·cm²). This measurement indicates that the corrosion resistance of aluminium alloy in these solutions is the lowest. Addition of zeolite/Zn(H₂PO₄)₂ pigments (at a concentration of 1 g/l) to the corrosion solution leads to the increase of the impedance modulus. It should be noted that the highest efficiency of corrosion inhibition by zeolite/Zn(H₂PO₄)₂ pigment are at a 1:1 and 3:1 components ratio.

The use of separate inhibitory components of the mixture does not ensure high efficiency of anti-corrosion protection of the alloy.





The obtained pigments can become promising inhibitory components of paint primers for the protection of aluminium alloy structures in an industrial environment and serve as an effective alternative to the known zinc phosphate pigments.

Acknowledgements

Lviv Ukraine 25.08-27.08.2022

The work was performed within the project No. 2020.02/0063 "Synthesis and properties of new complex anti-corrosion pigments for paint coatings based on aluminosilicate nanocontainers" of the National Research Foundation of Ukraine.